



Application Instructions

DESCRIPTION: Construct Wrap **general ht** is a high-quality interior water-based, peelable coating specifically designed for the protection of non-porous substrates during the construction phase. Construct Wrap **general ht** has been developed for high temperature and high humidity climates of 18°-40°. Construct Wrap **general ht** has very high scratch and impact resistance, designed to withstand foot traffic scuffing and acting as a permanent 'drop sheet'.

USES: Suitable for porcelain, granite or vitrified tiles and bench tops, stainless steel, 2-pac coatings, laminex, fiberglass, enameled or painted metals or other sealed non-porous surfaces.

APPLICATION:

- Do not apply to tile grout width above 3mm unless sealed
- Apply within temperature range of 10 – 40°C
- Stir Construct Wrap **general ht** lightly prior to use
- Construct Wrap **general ht** must NOT be watered down
- Construct Wrap **general ht** should be applied to clean, dry non-porous surfaces only
- ALWAYS apply a trial patch first as it is sometimes difficult to determine the surface type.
- Use a clean, dry 12mm nap paint roller approximately 180mm wide and clean tray to suit
- Always apply masking tape where finished edge ends, maintaining a thick coat for ease of peeling. Peel masking tape off while product is still wet
- Recommended coating thickness of 200µm per coat wet (twice the thickness of exterior paint). Applied any thinner and Construct Wrap **general ht** will be more difficult to peel off and will require a considerable amount of extra cleaning time
- Avoid Construct Wrap **general ht** entering channels, crevices and gaps
- Minimum of two coats are recommended for heavy traffic or high impact areas
- Allow 2 hours for first coat to dry before applying additional coats

CURING:

- Construct Wrap **general ht** dries in under an hour @ 20°C but requires 72 hours to cure prior to peeling off surface, depending on temperature, humidity and air movement

COVERAGE:

- Approximately 3-5 m² per litre per coat @ 100-120 micron

CLEAN UP: Water

PRODUCT LIFE:

- Construct Wrap **general ht** has limited UV stable properties, it has a surface life of a minimum 6-9 months in normal interior conditions

REMOVAL:

- Remove in normal mild weather conditions preferably out of direct sunlight
- Do not remove in air or surface temperatures are below 10°C
- Apply water to the coated surface prior to peeling with either a brush, sponge or hose to assist in lowering the temperature for ease of peeling if temperatures are above 30°C
- Starting from one corner, gently peel off Construct Wrap **general ht** trying to keep it in one piece
- If required, use additional water to remove the remaining Construct Wrap **general ht**
- A high pressure hose will assist in the removal of Construct Wrap **general ht** if it has been applied to thinly or been over exposed to weather
- Following removal, it is very important to ensure all residue has been cleaned off other porous surfaces (paths, driveways or walls) to prevent Construct Wrap **general ht** baking on or adhering to substrates
- Dispose of waste responsibly

STORAGE & HANDLING:

- Refer to MSDS

HEALTH & SAFETY:

- Refer to MSDS

CONTACT INFORMATION:

Manufacturer: Skudo Coatings Pty Ltd PO Box 148 Robina Queensland 4226 Ph: 1300 795 997 Fax: 07 55379429

The application, use and processing of our products is the responsibility of the user. Any technical or other advice, information or data provided by us, whether verbally, in writing or by way of trials of tests, is given without guarantee or warranty. Refer to Material Safety Data Sheets for information on Storage & Handling, Health & Safety and Transport.